



Effect of Machining on 410 Martensitic Stainless Steel: A Review

Mukesh Kumar^{1*}, Dr. Manish Gangil²

¹M.Tech Student, ²Professor

^{1,2} Department of Mechanical Engineering

Department of Mechanical Engineering, SSSCE, RKDF, University Bhopal, (M.P.) India ¹jimukeshkumarje@gmail.com, ²rkdfbjopal@gmail.com

* Corresponding Author: Author Name

ABSTRACT

Abstract. Machining takes place when a part of undesirable material ranging from metals, polymer, and wood to ceramic or even composite is removed from a part to give a better shape and design. The parts that are machined are called work piece and undesirable materials are called the chips. The machining process is in three forms which are the conventional (traditional) process, abrasive process and non-traditional processes. This review paper focused on the various forms of machining in stainless steel, based on the machine able family. Stainless found the way into various applications resulting in their wide usage which include equipment in the industries, equipment's in beverage and food, automotive trim and cookware. This paper aims at opening more light on the importance of stainless steel during machining operations.

Keywords : Chips, corrosion, machining, 410 Martensitic Stainless Steel, tools.

Introduction

Machining takes place when a part of undesirable material ranging from metals, polymer, and wood to ceramic or even composite is removed from a part to give a better shape and design. The parts that are machined are called work piece and undesirable materials are called the chips. The machining process is in three forms which are the conventional (traditional) process, abrasive process and nontraditional processes . During the process of machining ablation and evaporation mostly takes place leading to the wearing out of the work piece [1].

Machining operations take place using the conventional (traditional) processes, this operation comprises of milling, drilling, boring, turning and much more. In the contemporary industry, abrasive processes are very important cutting processes, such as grinding, lapping and polishing. Other forms of cutting processes involve the use of chemical energy to remove material from work piece thereby avoiding physical contact between the work piece and the tools, this form of processes are called nontraditional machining operation and they consist of machining electro discharge or, machining for electrochemical, water machining for water jet, ultrasonic machining and laser machining [2].

Machining is utilized in the treatment of various modern areas; it is the treatment of work pieces into perfect surface finish characterized by roughness, texture, residual stresses and microstructure using dimensional measurement Performance and yield of a metal in an assembling industry relies greatly on the metal cutting processes which can only be achieved through perfect machining process. These processes have been used over the years and improvements are taking place from time to time, metals like aluminum, carbon steel, stainless steel and much more, has been worked on and stainless steels are preferred than other metals due to their characteristics [4]

Stainless steel is more preferred because it rewards both producer and client with benefits like Heat and Corrosion Resistance, Durability, Appearance, Strength, Fabrication Flexibility, Low Maintenance. Examples of iron-based composites are Stainless steels which consist of 10.5 per cent chromium or more. some Extra alloying components will also be included for the duration of liquefying, the example of some metals are used to improve some properties and also qualities, these metals are columbium, nickel, titanium and molybdenum. 410 Martensitic Stainless steels serve as significant application ranging from machinery and equipment for tough industrial environments to brightly polished consumer products to machine [5]. According to metallurgical structure, there are several types of stainless steel, of stainless steel are categories into five (5) parts; they are austenitic, ferritic, martensitic, precipitation and duplex. Which has nowadays offers genuine forms of material goods ranging from an extensive choice of types preferably right for machining or extra fabrication processes to particularly formulated alloys capable of being developed in the most challenging surroundings. 410 Martensitic Stainless Steels can be machined utilizing properties fit for meeting a wide scope of assembling and end-user necessities which are, cold shaped, forged, expelled, or welded by contemporary manufacturing instruments and procedures [6].

2. Corrosion Resistance

The impact of chromium as an element of the alloy has contributed to the corrosion resistance quality of 410 Martensitic Stainless stainless steel. Thin, transparent chromium oxides are formed when it is combined with oxygen to protect the metal surface. To improve chromium oxide film molybdenum, nickel and chromium and some important alloying elements must be improved so that it can be protective and stable in a mild aqueous environment and the normal atmosphere. Resistance penetration of chloride can be achieved by adding molybdenum and chromium thereby improve the film stability, and in a strong acid environments nickel improves film resistance. With the help of oxygen in the environment, the protective film will reform itself in the case of disturbance or destruction and still continue to give maximum protection [7].

2.1 High-Temperature Corrosion Resistance

In elevated-temperature service 410 Martensitic Stainless steel has been widely used, concerning their resistance to corrosion some changes do occur in chromium oxide film protection. For instance, a protective oxide film is formed when an oxidizing gas is slightly increased in temperature. The film will be in the form of sulfide serving as protection in an environment containing sulfur bearing gases. Depending on the alloy content in an environment, In more aggressive environments the sudden increase in scaling may occur due to surface film breakdown under a temperature above 1600°F. At a point of limit where the film can no longer heal itself, the film breaks down and loses its protective strength due to high temperature and corrosion [8].

2.2 Thermal Stability

Evaluation of changes in metallurgical structure was carried out because of the period in use and rate of temperature on any type of steel or alloy can be expected. Precipitations of carbide embrittlement or softening are examples of changes that take place. Softening occurs at the point where the exposure of martensitic 410 Martensitic Stainless steel to temperature is approaching or exceeding the original hardening temperature. In order not to lose the high hardness of Type 440 °C the temperature is held at 900°F for a short period [9].

2.3 Embrittlement

Changes in metallurgical structure of any 410 Martensitic Stainless steel and alloy can occur due to the effect of time and temperature; these changes can be softening, embrittlement or carbide precipitation. When martensitic steel is exposed to the temperature approaching or exceeding the original hardening temperature then softening will occur. To retain the high hardness of Type 440 °C the temperature has to be held at 900°F for a little time. At elevated temperature, austenitic stainless steel which is cold worked can be softened. Delicate equipment needs to be handled with care during maintenance so as not to be affected by embrittlement which is caused by loss of toughness at room temperature. High-temperature properties, thermal stability, hot strength and Physical properties are very important during the analysis of stainless steel [10].

2.4 Advantages of 410 Martensitic Stainless Steel in a Corrosive Environment

There are various types of corrosive environments and they are characterized by the rate of temperature, chemicals and their concentration, flow rate, time and atmospheric conditions. To avoid using the wrong tool for the right process of machining the relationship between the stainless steel and its environment will be considered. However, the most readily available and Types 304, 430, or 410 are the most widely used stainless steels. Type 304 can be applied in different applications, in the food processing environment it is a strong resistance in architectural construction it withstands rust, it can withstand various types of inorganic materials, it opposes dyestuffs and organic chemicals. However, at high chloride, high acid and high-temperature condition, the protective rate will be reduced [11].

At moderate temperature and concentrations, Type 304 withstands sulfuric acid and nitric acid, equipment such as liquefied gases, consumer product, wastewater treatment transportation, equipment used in the kitchen and many more are low-temperature equipment and it is used to store them. In an environment that tends to cause pitting Type 316 is better than Type 304 in such corrosion resistance, due to the presence of more nickel and 2 - 3 per cent of molybdenum. Type 304 has been used widely in process industries because it develops high resistance against sulfuric acid [12].

Type 317 prevent pitting and it is better than Type 316 due to the presence of molybdenum having 3 - 4 per cent and much more chromium, also Type 430 is used in nitric acid and also for polishing trim applications in the mild atmosphere because it has lower alloy contents. Type 410 is used for the combination of corrosion resistance of highly stressed parts such as fasteners due to its very low alloy content for general purpose stainless steel. It also prevents corrosion in mild chemical environments, mild atmosphere and steam environments [13].

3. The Machinable Family of 410 Martensitic Stainless Steels

The misconception on machinability by Machine shop operators are diverse, however surface finish, cutting speed, and tool life are the important one to the other in metal machinability. The Machinability of stainless steels is unique and is different from other metals, and carbon or alloy steels. Stainless steel poses a significant challenge for micro-manufacturing technologies, for the reason that it is hard to machine, however it is being used progressively to make micro components. In order to improve the machinability of stainless steel the composition must be altered and the addition of

nonmetallic in other increase the nature of the structure of austenitic stainless steel. Material such as selenium, tellurium, lead and sulfur is introduced into the metals due to the difficulty in machining. This addition gives rise to form free machining elements [14].

3.1 Free-machining 410 Martensitic Stainless Steels

Machining characteristics of 410 Martensitic stainless steels can be achieved through alloying elements such as selenium, copper, sculpture, lead; phosphorus or aluminum during melting point can be adjusted or added. To reduce the possibility of chips to weld the tool, by introducing alloy elements the friction between the tool and the work piece can be reduced. Also when sulphur is added to the work piece it reduces transverse ductility and the friction force of the chips causing do to break off more easily. Machinable & Stainless, (Improvement has been made in the machinability of stainless steels thereby introducing the free machining stainless steel of types 303, 303 Se, 430 °F, 416, and 420 °F [15].

3.2 The Machinability of often Utilized 410 Martensitic Stainless Steels and There Free-Machining

The adverse effects of the free machine are weld ability, transverse ductility, corrosion resistance and more. The grades of Free-machining is mostly use based on the environment they are suitable for them to achieve a higher productivity rate if the right grade tool is used for the right machining processes. Type 303 and 303Se of free machine stainless steel was evaluated by Zhu, Chen, Xu, Gu and Zhao 2016, they discovered the one which has higher cutting speeds and is well suited for screw machining operations resulting in longer tool life and higher productivity, in comparison to Type 304 (austenitic-18Cr-8Ni). Scratching are prevented in the moving parts of Type 303 because of their no galling properties thereby making disassembly of past easily. They are much applicable in valves fitting valve bodies, shafting, valve trim, etc. while Type 303 Se are applicable in hot and cold working operations with better formability and corrosion resistance compared with type303 however they are similar in applications [2].

3.2.1 Machining Characteristics

Investigation on Types 303 and 303 Se stainless plates of steel was carried out by Sullivan and Cottrell 2002 [15] and discovered the speeds to be used should be between 102 - 130 surface feet per minute in turning operations, due to cold working the machinability of the machine increases resulting in satisfactorily performed polishing and grinding operations which produces brittle chips and are easily machined. The machinability rating of Types 303 and 303 Se is an average of 75 per cent when compared to Type 416. Type 303 and type 304 was compared by irapattarasilp and Kuptanawin 2012 [28] and discovered the best possible machining rate should be considered first, knowing fully well that type 304 has corrosion resistance and strength but lacks speed and accuracy which makes Type 303 a modifier of Type 304 with chromium, nickel, and sulphur contents and 25 - 30 per cent faster than Type 304.

Type 303Se, is the variation of free machine Type 304, the sulphur content is replaced with selenium when cold working is to occur, Type 303 Se is better than 303 in machined surface finish, the cold working involves swinging, severe thread rolling and staking. The 400 series stainless sheets of steel were examined by [3], there are also free-machining alterative to consider. During machining Type 430 °F is preferred to type 430 because type 430 °F is adjusted to enhance the machining characteristics by preserving the work piece for a long time. Free machining variation of Type 420 is Type 420 °F and that of Type 410 is Type 416 °F.

4. Conclusion

In this review, the characteristics of 410 Martensitic Stainless steel as metal and its alloy was examined, their differences and their applications in various aspects of manufacturing sectors was also evaluated. The availability of 410 Martensitic Stainless steel from different grade becomes essential due to the constant improvement in their alloys over corrosion resistance, machinability and welder ability, which makes stainless steel one of the most used metal, however 410 Martensitic Stainless steel in its grade are applicable to different industrial purposes that means a particular grade cannot be used for multipurpose as compared to other metallic alloys.

References

- [1] Benardos, P. G., & Vosniakos, G. C. (2003). Predicting surface roughness in machining a review International Journal of Machine Tools and Manufacture, 43(8) 833-844.
- [2] O'Sullivan, D., & Cotterell, M. (2002). Machinability of austenitic stainless steel SS303. Journal of Materials Processing Technology, 124(1-2), 153-159.
- [3] Won, C. H., Jang, J. H., Kim, S. D., Moon, J., Ha, H. Y., Kang, J. Y., ... & Kang, N. (2019).Effect of annealing on mechanical properties and microstructure evolution of borated stainless steels. Journal of Nuclear Materials, 515, 206-214.
- [4] Krall, S., Reiter, M., & Bleicher, F. (2018). Influence of the machine hammer peening technology on the surface near material structure of stainless steel XsCrNi18-1 O. Materials Today Proceedings, 5(13), 26603-26608.
- [5] Bissey-Breton, S., Vigna, Herbst, F., & Coudert, J. B. (2016). Influence of machining on the microstructure, mechanical properties and corrosion behaviour of a low carbon martensitic stainless steel. Procedia Cirp, 46(1), 331-335.
- [6] Hoier, P., Malakizadi, A., Friebe, S., Klement, u., & Krajinik, P. (2019). Microstructural variations in 31 6L austenitic stainless steel and their influence on tool wear in machining. Wear, 428, 315-327.

- [7] Ravitej, S. v., Murthy, M., & Krishnappa, M. (2018). Review paper on optimization of process parameters in turning Custom 465® precipitation hardened stainless steel. *Materials Today Proceedings*, 5(1), 2787-2794.
- [8] Laleh, M., Hughes, A E., Xu, W., Haghddadi, N., Wang, K., Cizek, P., & Tan, M. Y. (2019). On the unusual intergranular corrosion resistance of 316L stainless steel additively manufactured by selective laser melting. *Corrosion Science*, 161, 108189.
- [9] Novovic, D., Dewes, R. c., Aspinwall, D. K., Voice, W., & Bowen, P. (2004). The effect of machined topography and integrity on fatigue life. *International Journal of Machine Tools and Manufacture*, 44(2-3), 125-134.
- [10] Bagaber, S. A., & Yusoff, A R. (2018). Sustainable Optimization of Dry Turning of Stainless Steel based on Energy Consumption and Machining Cost. *Procedia CIRP*, 77, 397-400
- [11]. Kumar Hemant Dave Kush and Gangil Manish "An Assessment of Duplex stainless Steel pipe for Oil and Gas Application" *Research Journal of Engineering Technology and Management* (ISSN:2582-0028) Volume 2, Issue 3, September 2019.
- [12]. Sah Ram Balak and Gangil Manish "Optimization Design of EDM Machining Parameter for Carbon Fibre Nano Composite" *Research Journal of Engineering Technology and Management* (ISSN:2582-0028) Volume 2, Issue 3, September 2019.
- [13].Kantilal Patel Bhaumik and Gangil Manish "Scope for Structural Strength Improvement of Compressor Base Frame Skid" *Research Journal of Encoineering Technology and Management* (ISSN: 2582-0028)Volume 2, Issue 2, June 2019.
- [14].Kantilal Patel Bhaurnik and Gangil Manish "Recent Innovations for Structural Performance Improvement of Cotter Joint" *Research Journal of Engineering Technology and Management* (ISSN: 2582-0028) Volume 2, Issue 2, June 2019.
- [15]. Tanel Hirenkumar Vishnubhai and Gangil Manish "Recent Innovations for Structural Performance Improvement of Plummer Block" *Research Journal of Engineering Technology and Management* (ISSN: 2582-0028) Volume 2, Issue 2, June 2019.